

Material: South Germany heavy bovine, wet blue 1.4-1.6 mm

Process: Washing wet blue (percentages on wet blue weight)
1% **PROSPREAD** + 1% **PRODEGREAZE** (*eliminated oxalic acid and surfactant*)

Results: No foam with Proviaera.

- Visual assessment in crust: No significant differences were observed.

Conclusion: Comparable quality achieved. Proviaera's process reduced COD and reduced water usage while eliminating surfactants and a strong dicarboxylic acid.



Foaming

Customer: Tannery in Germany